

Bisca-Stic CEH-13 technical data sheet

REFERENCE:	BISCA-STIC CEH-13			
PRODUCT PROPERTIES	TEST STANDARD		VALUES	UNITS
Base film			UHMW polyethelene	
Weight without adhesive	ASTM D751-00	± 5%	120	g/m2
Thickness without adhesive	ASTM D751-00		0.127	mm
Thickness without liner			0.18	mm
Surface texture			Smooth non-stick	
Adhesive type			Rubber resin	
Adhesion	ASTM D751-00		725	g/cm
Maximum temperature			52	°C
Elongation			225	%
Maximum width			610	mm

Note: various widths are available, please contact our sales team to make your enquiry, details are available upon request.

Values shown are typical and are subject to change without notice. Before using, the user should determine the suitability of the product for its intended use and assumes all risk and liability in connection therewith. Specifications are subject to change without notice.

Weight tolerance g/m2 ± 5% variation.