

Reference:	Goldweld ADH			
Product properties	Test standard		Values	Units
Coating %			69	
Weight without adhesive	ASTM D751-00	± 5%	320	g/m2
Weight including liner	ASTM D751-00		465	g/m2
Thickness without adhesive	ASTM D751-00		0.17	mm
Thickness without liner	ASTM D751-00		0.22	mm
Breaking strength	ASTM D751-00	warp	200	N/cm
		weft	150	N/cm
Tearing strength	ASTM D751-00	warp	8	N
		weft	8	N
Surface texture		Smooth non-stick		
Adhesive type		Silicone PSA		
Adhesion	ASTM D751-00		4	N/cm2
Adhesive temperature resistance			-73 to +240	°C
Glass style properties	Test standard		Values	Units
Glass style reference			2116	
Filament Diameter	DIN EN12654	warp	EC7	micron
		weft	EC7	micron
Yarn count	DIN EN 12654	warp	22	Tex
		weft	22	Tex
Fabric construction	DIN EN 1049	warp	24	Ends/cm
		weft	23	Picks/cm
Weave pattern	DIN ISO 9354		Plain	
Fabric thickness	DIN ISO 4603/E		0.09	mm
Base weight	DIN EN 12127	± 5%	107	g/m2

Note: various widths are available, please contact our sales team to make your enquiry, details are available upon request.

Values shown are typical and are subject to change without notice. Before using, the user should determine the suitability of the product for its intended use and assumes all risk and liability in connection therewith. Specifications are subject to change without notice.

Weight tolerance g/m2 ± 5% variation.
Teflon® content ±2% variation.

Goldweld is manufactured and distributed by Biscor Limited:

Goldweld.co.uk
Biscor Limited
Unit 8
Kingsmark Freeway
Bradford
West Yorkshire
BD12 7HW

T: +44(0)800 0731 148

F: +44 (0)1274 694685

E: info@goldweld.co.uk

W: www.goldweld.co.uk



Teflon® is a registered trademark of DuPont™.