

Bisca-Stic SPF 13 technical data sheet

REFERENCE:	BISCA-STIC SPF 13			
PRODUCT PROPERTIES	TEST STANDARD		VALUES	UNITS
Base film			Virgin skived PTFE	
Weight without adhesive	ASTM D751-00	± 5%	298	g/m ²
Weight including liner			445	g/m ²
Thickness without adhesive	ASTM D751-00		0.127	mm
Thickness without liner			0.192	mm
Surface texture			Smooth non-stick	
Adhesive type			Silicone PSA	
Adhesion	ASTM D751-00		5.5	N/cm
Adhesive temperature resistance			-73 to +240	°C
Elongation			275	%
Dielectric strength			14000	V
Operating class			180	°C

Note: various widths are available, please contact our sales team to make your enquiry, details are available upon request.

Values shown are typical and are subject to change without notice. Before using, the user should determine the suitability of the product for its intended use and assumes all risk and liability in connection therewith. Specifications are subject to change without notice.

Weight tolerance g/m² ± 5% variation.