

Bisca-Bake 5 technical data sheet

| REFERENCE: | | BISCA-BAKE 5 | | |
|------------------------|----------------|------------------|--------|------------------|
| PRODUCT PROPERTIES | TEST STANDARD | | VALUES | UNITS |
| Coating % | | | 56 | |
| Coated weight | ASTM D751-00 | ± 5% | 240 | g/m ² |
| Total thickness | ASTM D751-00 | | 0.109 | mm |
| Breaking strength | ASTM D751-00 | warp | 160 | N/cm |
| | | weft | 120 | N/cm |
| Tearing strength | ASTM D751-00 | warp | 10 | N |
| | | weft | 7 | N |
| Surface texture | | Smooth non-stick | | |
| GLASS STYLE PROPERTIES | TEST STANDARD | | VALUES | UNITS |
| Glass style reference | | | 2116 | |
| Filament Diameter | DIN EN 12654 | warp | EC7 | micron |
| | | weft | EC7 | micron |
| Yarn count | DIN EN 12654 | warp | 22 | Tex |
| | | weft | 22 | Tex |
| Fabric construction | DIN EN 1049 | warp | 24 | Ends/cm |
| | | weft | 23 | Picks/cm |
| Weave pattern | DIN ISO 9354 | Plain | | |
| Fabric thickness | DIN ISO 4603/E | | 0.09 | mm |
| Base weight | DIN EN 12127 | ± 5% | 107 | g/m ² |

Note: various widths are available, please contact our sales team to make your enquiry, details are available upon request.

Values shown are typical and are subject to change without notice. Before using, the user should determine the suitability of the product for its intended use and assumes all risk and liability in connection therewith. Specifications are subject to change without notice.

Weight tolerance g/m² ± 5% variation.

Teflon® content ±2% variation.