

Bisca-Tex 71-1100 technical data sheet

REFERENCE:		BISCA-TEX 71-1100		
PRODUCT PROPERTIES	TEST STANDARD		VALUES	UNITS
Coating %			43	
Coated weight	ASTM D751-00	± 5%	1087	g/m ²
Total thickness	ASTM D751-00		0.67	mm
Breaking strength	ASTM D751-00	warp	300	N/cm
		weft	250	N/cm
Tearing strength	ASTM D751-00	warp	68	N
		weft	48	N
Surface texture		Smooth non-stick		
GLASS STYLE PROPERTIES	TEST STANDARD		VALUES	UNITS
Glass style reference			166	
Filament Diameter	DIN EN 12654	warp	EC9	micron
		weft	EC9	micron
Yarn count	DIN EN 12654	warp	136x2	Tex
		weft	136x2	Tex
Fabric construction	DIN EN 1049	warp	11	Ends/cm
		weft	10.5	Picks/cm
Weave pattern	DIN ISO 9354	Plain		
Fabric thickness	DIN ISO 4603/E		0.9	mm
Base weight	DIN EN 12127	± 5%	620	g/m ²

Note: various widths are available, please contact our sales team to make your enquiry, details are available upon request.

Values shown are typical and are subject to change without notice. Before using, the user should determine the suitability of the product for its intended use and assumes all risk and liability in connection therewith. Specifications are subject to change without notice.

Weight tolerance g/m² ± 5% variation.

Teflon® content ±2% variation.