

Bisca-Tex K11-170 technical data sheet

REFERENCE:		BISCA-TEX K12-360		
PRODUCT PROPERTIES	TEST STANDARD		VALUES	UNITS
Coating %			73	
Coated weight	ASTM D751-00	± 5%	180	g/m ²
Total thickness	ASTM D751-00		0.10	mm
Breaking strength	ASTM D751-00	warp	400	N/cm
		weft	300	N/cm
Tearing strength	ASTM D751-00	warp	n/a	N
		weft	n/a	N
Surface texture		smooth		
ARAMID STYLE PROPERTIES	TEST STANDARD		VALUES	UNITS
Filament Diameter	DIN EN 12654	warp	Con.fil	micron
		weft	Con.fil	micron
Yarn count	DIN EN 12654	warp	44	Tex
		weft	44	Tex
Fabric construction	DIN EN 1049	warp	12.2	Ends/cm
		weft	12.2	Picks/cm
Weave pattern	DIN ISO 9354	Plain		
Base weight	DIN EN 12127	± 5%	110	g/m ²

Note: various widths are available, please contact our sales team to make your enquiry, details are available upon request.

Values shown are typical and are subject to change without notice. Before using, the user should determine the suitability of the product for its intended use and assumes all risk and liability in connection therewith. Specifications are subject to change without notice.

Weight tolerance g/m² ± 5% variation.

Teflon® content ±2% variation.